

APCOSIL 605 IZ / APCOSIL 602

PRODUCT DESCRIPTION

A two component solvent based moisture curing inorganic zinc silicate coating

FEATURES & RECOMMENDED USE

- Designed as primer coat for application in highly aggressive environments
- Excellent solvent resistance
- Good resistance to saline and marine atmosphere
- Can withstand substrate temperatures from -90°C to + 600°C
- Not suitable for immersion in alkaline (more than pH 9) or acidic (less than pH 5) liquids without suitable topcoats

TECHNICAL DATA

Colour	Grey
Gloss	Matt
Recommended DFT / Coat	50 – 75 µm
Theoretical Coverage Capacity	11.0 sq.mtr/lit @ 50 µm DFT 7.33 sq.mtr/lit @ 75 µm DFT
Drying time at 30°C	Surface dry : 30 minutes Hard dry : 16 hours Full cure : 7 days
Over coating interval at 30°C	Min. : 16 hours Max. : Max. Unlimited, provided surface is free from any contamination, corrosion and zinc salt
Method of Application	Air spray & Airless spray

The data given is for guideline only. The physical values are subject to normal manufacturing tolerances, colour and testing variances. The actual drying time/ overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc. The information provided above is at 30°C and 65% relative humidity.

DIRECTIONS FOR USE

Surface Preparation

General

- Surfaces must be dry, clean and free from contaminants
- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Oil and grease should be removed as per SSPC-SP1 solvent cleaning
- Surface should be checked and treated in accordance with ISO 8504 prior to priming

Blast Cleaning

- Steel, abrasive blast clean to min. Sa 2.5 Swedish specification. In case oxidation has occurred between blasting and application of Apcosil 605 IZ the surface should be re-blasted. A blasting profile of (Rz) 40-70 µm is recommended.
- Galvanised steel; sweep blast to roughen the surface and to remove any zinc salts that may be present
- Heavily pitted steel is not acceptable

Application Conditions

- Substrate temperature should be at least 3°C above dew point but not above 50°C
- Relative humidity should be above 50%
- Good ventilation is required in confined areas to ensure proper curing

Special Instructions

- Maintain constant agitation of the mixture until the batch is depleted
- The spray gun should be at a sufficient distance from the surface to get a wet and smooth coating after application. Besides using a correct spray technique, the amount of thinner added must be carefully adjusted to secure optimum film formation. The coating must be wet and smooth just after application
- Please refer to field guidelines for the inorganic zinc silicate coatings for further details

Mixing

- Apcosil 605 IZ / Apcosil 602 is supplied in 2 packs, liquid component (hydrolysate) and a powder component (zinc dust)
- Do not open packing until just before use. Loosen the settled material in the liquid portion, if any, with the help of hand stirrer followed by power stirrer for quick homogeneous mixing
- Add zinc dust gradually to the hydrolysate under stirring. Continue stirring until mixture is homogeneous (Do not mix in reverse order. It may result in lump formation in the paint)
- Strain mixture through a 30-60 mesh screen. Maintain constant agitation of the mixture until the batch is depleted. Once the unit has been mixed, it should be consumed within the working pot life

Mixing Ratio (By weight)	Hydrolysate : Zinc dust (Liquid) : (Powder) 60 : 40
Induction Time	None
Pot Life at 30°C	6 hours

Application

Brush / Roller	Not recommended
Air spray Recommended thinner Volume of thinner Nozzle orifice Nozzle pressure	T - 144 10 - 25% * 2.0 - 3.0 mm 0.3 - 0.4 MPa (approx. 3-4 atm; 43-57 p.s.i)
Airless Spray Recommended thinner Volume of thinner Nozzle orifice Nozzle pressure	T - 144 10 - 25% * 0.48 - 0.64 mm 15 MPa (approx. 150atm; 2100 p.s.i)

**Note: Depending on recommended thickness & application condition*

Cleaning

- Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipment's immediately after use with Thinner T 144. All surplus material and empty containers should be disposed off in accordance with appropriate regional legislation.

Product Characteristics

- While application, the spray gun should be at a sufficient distance from the surface to get a wet and smooth coating. Besides using a correct spray technique, the amount of thinner added must be carefully adjusted to secure optimum film formation. The coating must be wet and smooth just after application
- Inorganic zinc silicate primers are sensitive to environmental conditions for drying and curing. This product requires minimum relative humidity of 50% and minimum steel temperature should be 10° C. In case skin temperature of steel is more than 40° C spraying shall be done by extra thinning to avoid dry spray application. At Relative humidity below 50%, curing will be severely retarded. The curing at low humidity may be promoted by spraying fresh water after 4-6 hours of application of primer and keeping the surface constantly wet until curing is complete
- High deposition of film thickness (>125 microns) can result into mud-cracking while lower dry film thickness can affect the performance of coating. In case of mud cracking, complete removal of the affected areas by abrasive blasting and re-application as per original specification is recommended
- Untopcoated Apcosil 605 IZ is not suitable for immersion in alkaline (more than pH 9) or acidic (less than pH 5) liquids without suitable topcoats

Over-coating and Topcoats

- Before over-coating with recommended topcoats, ensure Apcosil 605 IZ / Apcosil 602 is completely cured. The complete curing can be checked as per ASTM 4752 i.e. 50 double rub of the coating with a cotton cloth soaked in thinner T 144 or MEK. If the coating remains unaffected, the curing is complete
- Prior to over-coating, Apcosil 605 IZ / Apcosil 602 must be clean, dry and free from soluble salts and zinc corrosion products. Zinc silicate primers, when exposed for extended periods of time without proper top coating, will start showing white rust formation. These “white rust” spots are zinc corrosion products. The extent of white rust formation will depend on the period of exposure of the zinc silicate coating and the nature of the surrounding environment. Prior to application of the subsequent coats, it is necessary to ensure removal of the white rust
- Zinc silicate coatings are porous and hence pinholes may occur in the subsequent coat due to solvent popping. To minimize pinholes, apply a mist coat as the first pass of the subsequent coat, let the entrapped air escape and then apply full coat
- Apcosil 605 IZ / Apcosil 602 may be topcoated with epoxies, chlororubber, acrylics, polysiloxanes, heat resistant silicones and others as recommended by Asian Paints PPG representative

PACK SIZE	20 L
STORAGE	Shelf Life: At least 6 months at 30° C for original unopened pack, subject to inspection thereafter Store in a cool, dry place and in accordance with local regulations
REGULATORY INFORMATION	Flash point: Liquid - Not less than 15° C, Powder - Above 65° C VOC: 580 g/ ltr as per USA-EPA Method 24

SAFETY INFORMATION

- As a general safety measure, inhalation of solvent vapours or paint mist and contact of liquid paint with skin & eyes should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection is always recommended while spraying paint
- Please refer our Material Safety Data Sheet prior to using the product

Disclaimer: To the best of our knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product.

"APCOSIL" is Trademark of Asian Paints Ltd. | Licensed user : Asian Paints PPG Pvt. Ltd.

Head Office: Asian Paints PPG Private Limited, Plot No-5, Gaiwadi Industrial Estate, S.V. Road, Goregaon (W), Mumbai 400 062

Tel No: 022 6218 2700, **CIN:** U24110MH2011PTC220557, **Email:** customer-care.apppg@asianpaintsppg.com, **Website:** www.asianpaintsppg.com